



e-Catalogue

AC 30 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

AC 30 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

BINDER PROPERTY

STANDARD RANGE

TEST METHOD

MIN

MAX

Viscosity, 140°F (60°C)

2400

3600

ASTM D2171

Viscosity, 275°F (135°C)

250

-

ASTM D2171

Penetration, 77°F (25°C), 100g, 5sec

30

-

ASTM D5

Flash point, Cleveland open cup

232

-

ASTM D92

Solubility in trichloroethylene

99

-

ASTM D2042

Tests on residue from thin-film oven test :

Viscosity, 140°F (60°C)

-

15000

ASTM D2171

Ductility, 77°F (25°C), 5cm/min

15

-

ASTM D113