



AH 50 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

AH 50 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	Min	Max	
Penetration 25°C, 0.1 mm	40	60	ASTM D5
Flash point °C	250	-	ASTM D92
Density, 15°C, (kg/m³)	1	1.06	ASTM D70
Softening point, °C	48	-	ASTM D36
Ductility @15 °C, CM	100	-	ASTM D113
Ductility @10 °C, CM	40	-	ASTM D113
Solubility in Trichloroethylene (wt)%	99	-	ASTM D 2042
Penetration Index	-1.5	1	-
AFTER TFOT AT 163 °C ASTM D1754			
Loss on Heating	-0.8	0.8	ASTMD1754
Retained Penetration ,%	61	-	ASTM D5
Ductility, 10 °C, 5CM/Min	6	-	ASTM D113