


AH 90 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

AH 90 - TECHNICAL DATASHEET
ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

BINDER PROPERTY
STANDARD RANGE
TEST METHOD

Min

Max

Penetration 25°C, 0.1 mm

80

100

ASTM D5

Flash point °C

230

-

ASTM D92

Density, 15°C, (kg/m³)

1

1.06

ASTM D70

Softening point, °C

42

-

ASTM D36

Ductility @15 °C, CM

100

-

ASTM D113

Ductility @10 °C, CM

20

-

ASTM D113

Solubility in Trichloroethylene (wt)%

99

-

ASTM D 2042

Penetration Index

-1.5

1

-

AFTER TFOT AT 163 °C ASTM D1754

Loss on Heating

-0.8

0.8

ASTM D1754

Retained Penetration ,%

61

-

ASTM D5

Ductility, 10 °C, 5CM/Min

6

-

ASTM D113