



CAP 35-40 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Palletized Wooden Box

CAP 35-40 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	MIN	MAX	
Needle penetration 0,1mm ,25 DEG C	35	45	ASTM D5
Softening point on the ring and ball	52	-	ASTM D36
Flash point, DEG C	235	-	ASTM D92
Change of softening point after heating, not more than, DEG C	8	-	ASTM D36
Penetration index	-1.5	0.7	ASTM D36
Penetration at 163°C after heating ,%	-	60	ASTM D5
Mass variation after heating, %, not more than	-	0.5	ASTM D2872
Ductility at 25oC, (cm)	60	-	ASTM D113
Saylbolt Furol Viscosity at 135oC	192	-	ASTM E102
Saylbolt Furol Viscosity at 150oC	90	-	ASTM E102
Saylbolt Furol Viscosity at 177oC	40	150	ASTM E102
Brooksfeld Viscosity at 135oC, SP 21, 20 rpm ,	374	-	ASTM D4402
Brooksfeld Viscosity at 150oC, SP 21 ,	203	-	ASTM D4402
Brooksfeld Viscosity at 177oC , SP 21	76	285	ASTM D4402
Solubility in trichlorethylene, min (% mass)	99.5	-	ASTM D2042