



e-Catalogue

PENETRATION GRADE - 80/100

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

PENETRATION GRADE 80/100 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	Min	Max	
Penetration @ 25 c , 100gr , 5s , 0.1mm	80	100	ASTM D5
Flash point °C	230	-	ASTM D92
Softening point °C	41	-	ASTM D36
Ductility @25 °C	100	-	ASTM D113
Loss on heating (wt)%	-	0.2	ASTM D6
Drop in penetration after heating %	-	20	ASTM D5-D6
Specific gravity @ 25 °C	1.01	1.06	ASTM D70
Solubility in Trichloroethylene	99	-	ASTM D2042
Spot test	Negative		A.A.S.H.T.O 102