



C170 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

C 170 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	Min	Max	
Viscosity at 60°C, Pa.s	140	200	ASTM D2171
Viscosity at 135°C, Pa.s	0.25	0.45	ASTM D4402
Penetration 100g, 5s @ 25°C (p.u)	62	-	ASTM D5
Binder Density @ 25°C	1000	-	ASTM D70
Matter Insoluble in Toluene	-	1.0	ASTM D2042
Flash Point, Cleveland Open Cup	250	-	ASTM D92
Tests on residue from thin-film oven test			
Viscosity at 60° C (% of the original After RTFO treatment)	-	300	ASTM D2171