



C240 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

C 240 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

BINDER PROPERTY

STANDARD RANGE

TEST METHOD

Min

Max

Viscosity at 60°C, Pa.s

190

280

ASTM D2171

Viscosity at 135°C, Pa.s

0.32

0.55

ASTM D4402

Penetration 100g, 5s @ 25°C (p.u)

53

-

ASTM D5

Matter Insoluble in Toluene

-

1.0

ASTM D2042

Flash Point, Cleveland Open Cup

250

-

ASTM D92

Tests on residue from thin-film oven test

Viscosity at 60° C (% of the original After RTFO treatment)

-

300

ASTM D2171