



e-Catalogue

## C 320 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

## C 320 - TECHNICAL DATASHEET

## ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

## BINDER PROPERTY

## STANDARD RANGE

## TEST METHOD

Min

Max

Absolute viscosity at 60°C, Pa.S

260

380

ASTM D2171

Kinematic viscosity at 135°C, Pa.S

0.4

0.65

ASTM D2170

Penetration @25°C (77°F), 100gm, 5sec,0.1MM

40

-

ASTM D5

Flash Point,°C

250

-

ASTM D92

Matter insoluble in toluene,%Wt

-

1.0

ASTM D4072

## Tests on residue from thin film over test / RTFOT

Viscosity of residue at 60°C (% of original),Pa.s

-

300

ASTM D2171