



e-Catalogue

## C50- TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

## C50- TECHNICAL DATASHEET

## ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

## BINDER PROPERTY

## STANDARD RANGE

## TEST METHOD

Min

Max

Viscosity at 60°C, Pa.s

40

60

ASTM D2171

Viscosity at 135°C, Pa.s

0.2

0.3

ASTM D2170

Penetration @25°C (77°F), 100gm, 5sec, 0.1MM

130

-

ASTM D5

Flash Point Cleveland open cup ,°C

250

-

ASTM D92

Matter insoluble in toluene ,%Wt

-

1

ASTM D4072

## Tests on residue from thin-film oven test

Viscosity of residue at 60°C as % of original ,%

-

300

ASTM D2171