


VG 10 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

VG 10 - TECHNICAL DATASHEET
ENVIRONMENT CONDITIONS

Temperature: 25.0 C		Humidity: 12%	
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	MIN	MAX	
Absolute Viscosity, 60°C, poises	800	-	ASTM D4402
Kinematic Viscosity, 135°C, CST	250	-	ASTM D2170
Flash point, C	220	-	ASTM D93
Solubility in trichloroethylene, %	99.0	-	ASTM D2042
Penetration at 25°C	80	100	ASTM D5
Softening point, C	40	-	ASTM D36
Tests on residue from thin film over test / RTFOT			
Viscosity ratio at 60°C	-	4.0	ASTM D4402
Ductility at 25°C, cm, after thin film over test	75	-	ASTM D113