



e-Catalogue

VG 30 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

VG 30 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

BINDER PROPERTY

STANDARD RANGE

TEST METHOD

MIN

MAX

Absolute Viscosity, 60°C, poises

2400

-

ASTM D4402

Kinematic Viscosity, 135°C, CST

350

-

ASTM D2170

Flash point, C

220

-

ASTM D93

Solubility in trichloroethylene, %

99.0

-

ASTM D2042

Penetration at 25°C

50

70

ASTM D5

Softening point, C

47

-

ASTM D36

Tests on residue from thin film over test / RTFOT

Viscosity ratio at 60°C

-

4.0

ASTM D4402

Ductility at 25°C, cm, after thin film over test

40

-

ASTM D113