


MC 3000 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Framed Palletized Jumbo Bag

MC 3000 - TECHNICAL DATASHEET
ENVIRONMENT CONDITIONS
Temperature: 25.0 C
Humidity: 12%
BINDER PROPERTY
STANDARD RANGE
TEST METHOD
Min
Max
Kinematic viscosity at 60°C mm²/s
3000
6000
ASTM D2170
Flash point (tag open cup), °C
66
-
ASTM D3143
Distillation test
Distillate, volume percent of total Distillate to 680°F(360°C)
To 437°F(225°C)
-
-
ASTM D402
To 500°F(260°C)
-
15
ASTM D402
to 600°F(316°C)
15
75
ASTM D402
Residue from distillation to 680°F(360°C), percent volume by difference
80
ASTM D402
Test on Residue from distillation test
Penetration 77°F(25°C) 100g,5s mm
120
300
ASTM D5
Ductility 77°F(25°C) 5cm/min cm
100
-
ASTM D113
Solubility in trichloroethylene %
99
-
ASTM D2042
Water, percent volume
-
0.2
ASTM D95