



e-Catalogue

M4 - TECHNICAL DATASHEET

- 16KG Cartoon Box
- 20KG Bucket

M4 - TECHNICAL DATASHEET

Sample Certification

Sample Grade :	BERNET MASTIC BITUMEN (M4) (POLYMER MODIFIED BITUMEN) Sealing Concrete Tanks And Tunnels
Packing	kg Bucket 20 & kg Carton 16
Reference Number :	BERNET M4

Environment Condition

Temperature: 25 °C	Humidity: 28%
--------------------	---------------

Test Result

TEST PERFORMED	Standard Range		Test Method
	Min	Max	
Penetration @ 25 , 100gr , 5s , 0.1mm	20	-	ASTM D5
Softening point , °C	70	-	ASTM D36
SPGR @ 25 °C . Kg/cm3	1	-	ASTM D70
The temperature of the mixer mixture, C	170 ± 5		-
Mixture temperature in executive equipment, C	160-165		-
Maximum tail heating, C	180		-