


**CRMB 60 - TECHNICAL DATASHEET**

- 185KG Steel Drum
- 1MT Palletized Wooden Box

**CRMB 60 - TECHNICAL DATASHEET**
**ENVIRONMENT CONDITIONS**
**Temperature: 25.0 C**
**Humidity: 12%**
**BINDER PROPERTY**
**STANDARD RANGE**
**TEST METHOD**
**Min**
**Max**
**Penetration at 25 °C 1/10mm, 100g, 5 sec**
**-**
**50**
**ASTM D5**
**Softening Point, (R&B), °C**
**60**
**-**
**ASTM D36**
**Elastic Recovery at 15 °C, %**
**50**
**-**
**ASTM D6084**
**Flash point , COC, °C**
**220**
**-**
**ASTM D92**
**Separation, Difference in Softening Point, (R&B), °C**
**-**
**4**
**ASTM D7173**
**Viscosity at 150 °C, Poises**
**3**
**9**
**ASTM D2170/D4402**
**Thin Film Oven Test & Test on Residue**
**Loss in Mass, %**
**-**
**1.0**
**ASTM D6**
**Reduction in Penetration of residue at 25 °C , 100g, 5s, %**
**-**
**40**
**ASTM D5**
**Increase in Softening Point, °C**
**-**
**5**
**ASTM D36**
**Elastic Recovery at 25 °C, %**
**35**
**-**
**ASTM D6085**