



e-Catalogue

HYBRID MB - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Palletized Wooden Box

HYBRID MB - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C

Humidity: 12%

BINDER PROPERTY

STANDARD RANGE

TEST METHOD

MIN

MAX

Penetration @ 25 C° , 100gr , 5s , 0.1mm

30

70

AASHTO T49

Softening point , C°

70

-

AASHTO T53

Density @ 25 C° , gr/cm

-

1.2

AASHTO T228

Flash point , C°

220

-

AASHTO T48

Elastic Recovery @ 25 C° , 10cm Elongation .%

70

-

ASTM D6084

Test on Residue After TFOT

Change of Mass,%

-

1

AASHTO T47