



e-Catalogue

PMB 25/55-60 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Palletized Wooden Box

Polymer Modified Bitumen 25/55-60 - TECHNICAL DATASHEET

ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	MIN	MAX	
Penetration @ 25 c , 100gr , 5s , 0.1mm	25	55	EN 1426
Softening point, °C	60	-	EN 1427
Elastic recovery at 25 °C , %	60	-	EN 13398
Fraas breaking point, °C	-	-10	EN 13589 EN 13703
Force Ductility at 10 °C, J/cm2	2	-	EN ISO 2592
Flash point, °C	235	-	EN 1426
Retained penetration , %	60	-	EN 1427
Change in softening point, °C	-	8	EN 12607-1
Change of mass , %	-	0.5	EN 1426
Elastic recovery at 25 °C after EN 12607- , %	50	-	EN 13398
Storage stability: Difference in softening point, °C	-	5	EN 13399 EN 1427
Drop in softening point after EN 12607-1, °C	TBR (To Be Reported)		EN 12607-1 EN 1427