


PMB A-E1 - TECHNICAL DATASHEET

- 185KG Steel Drum
- 1MT Palletized Wooden Box

Polymer Modified Bitumen A-E1 - TECHNICAL DATASHEET
ENVIRONMENT CONDITIONS

Temperature: 25.0 C	Humidity: 12%		
BINDER PROPERTY	STANDARD RANGE		TEST METHOD
	MIN	MAX	
Softening Point , °C	55	65	ASTM D36
Viscosity at ,165 °C,Pa.s	-	0.6	ASTM D4402
Elastic recovery,15 °C, 10 CM	50	-	ASTM D6084
Storage stability at 180 °C, difference in softening point of top and bottom	-	5	ASTM D7173
Flash point, Cleveland Open Cup, minimum , °C	230	-	ASTM D92
Rolling Thin Film Oven Test (RTFOT)			
Mass change,%	-	1	ASTM D2872
Softening Point , °C	53	-	ASTM D36
Elastic recovery , 15 °C, 10 Cm ,%	40	-	ASTM D6084