


**PMB A-P1 - TECHNICAL DATASHEET**

- 185KG Steel Drum
- 1MT Palletized Wooden Box

**Polymer Modified Bitumen AP-1 - TECHNICAL DATASHEET**
**ENVIRONMENT CONDITIONS**

| Temperature: 25.0 C                                                          | Humidity: 12%  |      |             |
|------------------------------------------------------------------------------|----------------|------|-------------|
| BINDER PROPERTY                                                              | STANDARD RANGE |      | TEST METHOD |
|                                                                              | MIN            | MAX  |             |
| Softening Point , °C                                                         | 63             | 73   | ASTM D36    |
| Viscosity at ,165 °C,Pa.s                                                    | -              | 0.55 | ASTM D4402  |
| Elastic recovery,15 °C, 10 CM                                                | 30             | 50   | ASTM D6084  |
| Storage stability at 180 °C, difference in softening point of top and bottom | -              | 5    | ASTM D7173  |
| Flash point, Cleveland Open Cup, minimum , °C                                | 230            | -    | ASTM D92    |
| Rolling Thin Film Oven Test (RTFOT)                                          |                |      |             |
| Mass change,%                                                                | -              | 1    | ASTM D2872  |
| Softening Point , °C                                                         | 61             | -    | ASTM D36    |
| Elastic recovery , 15 °C, 10 Cm ,%                                           | Report         |      | ASTM D6084  |